

DYNAFLOW®

FORMULATED TO MIRROR THE CHARACTERISTICS OF STAY-SILV® 15

DESCRIPTION

This alloy contains considerably less silver, making it an excellent cost effective alternative to the 15% silver alloys. This premium, medium range silver alloy has been meticulously formulated to even tighter specifications than our standard copper-to-copper alloys.

PRODUCT	SOLIDUS	LIQUIDUS	FLUIDITY RATING
DYNAFLOW®	1190°F (643°C)	1459-1471°F (787-794°C)	3
STAY-SILV® 15%	1190°F (643°C)	1475°F (802°C)	3



A LINCOLN ELECTRIC COMPANY

The Harris Products Group
A Lincoln Electric Company
4501 Quality Place - Mason, OH 45040
Customer Service: 1.800.733.4043
Fax: 513.754.8778
www.harrisproductsgroup.com



Turn to the
DYNAFLOW® VS
STAY-SILV® 15 **Pros**