

INERTROD 308H

TOP FEATURES

- The higher carbon content results in higher strength at elevated temperatures.
- Excellent mechanical strength.
- It is used mainly in petrochemical industry, including the fabrication of pipe and vessel.

TYPICAL APPLICATIONS

- Petrochemical
- Pipes and vessels fabrication

CLASSIFICATION

AWS A5.9 ER308H
EN ISO 14343-A W 19 9 H

SHIELDING GASES (ACC. EN ISO 14175)

I1 Inert gas Ar (100%)

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, WIRE

C	Mn	Si	P	S	Cr	Ni
0.060	1.9	0.5	≤0.020	≤0.020	20	10

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Yield strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J)	
						+20°C	-10°C
Typical values	I1	AW	≥350	≥550	≥35	≥70	≥32

* AW = As welded

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Weight (kg)	Item number
2.4	PE Tube	5.0	W000283429

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.eu for any updated information.