

# 70CuNi

## TOP FEATURES

- Solid 70/30 cupronickel wire for TIG
- Match 70/30 base material in strength and color

## CLASSIFICATION

AWS A5.7M                      ERCuNi  
EN ISO 24373-A                S Cu 7158 / CuNi30Mn1FeTi

## SHIELDING GASES (ACC. EN ISO 14175)

I1                                      Inert gas Ar (100%)

## CHEMICAL COMPOSITION (WEIGHT %), TYPICAL

	Mn	Si	S	P	Cu	Ni	Fe	Ti	Pb	C
Min.	0.5				bal.	29.0	0.40	0.20		
Max.	1.0	0.25	0.01	0.02		32.0	0.7	0.50	0.02	0.04
Typical	0.8	0.01	0.005	0.003	67	31	0.5	0.3	0.001	0.03

## MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

As welded		Typical
Tensile strength	(MPa)	365
0.2% Proof strength	(MPa)	200
Elongation (%)	5d	40
Hardness	(HV)	105

## PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Weight (kg)	Item number
1.6	PE Tube	5.0	T70CUNI-16
2.4	PE Tube	5.0	T70CUNI-24

## TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.  
Please refer to [www.lincolnelectric.eu](http://www.lincolnelectric.eu) for any updated information.