

SUPERARC® L-59®

Mild Steel, Copper Coated ■ AWS ER70S-6



KEY FEATURES

- Engineered alloy system enhances silicon island management
- Minimal spatter
- Copper coated for long contact tip life
- Fast travel speeds
- MicroGuard® Ultra provides superior feeding and arc stability

WELDING POSITIONS

All

SHIELDING GAS

100% CO₂
 75-95% Argon / Balance CO₂
 95-98% Argon / Balance O₂
 Flow Rate: 30 - 50 CFH

CONFORMANCES

AWS A5.18/A5.18M:	ER70S-6
ASME SFA-A5.18:	ER70S-6
ABS:	3YSA (100 CO ₂ & Mixed)
DNV Grade:	III YMS H5 (Mixed)
BV Grade:	SA3YHHH (Mixed)
CWB/CSA W48-06:	ER49S-6
EN ISO 14341-B:	G 49A 3 C S6

TYPICAL APPLICATIONS

- Robotic or hard automation
- Automotive
- Pipeline & Offshore
- Pressure vessels
- Heavy fabrication
- Alternative to metal-cored wire

DIAMETERS / PACKAGING

Diameter in (mm)	33 lb (14.9 kg) Plastic Spool	44 lb (20 kg) Fiber Spool	44 lb (20 kg) Steel Spool	60 lb (27.2 kg) Fiber Spool	500 lb (227 kg) Accu-Pak® Box
0.035 (0.9)	ED034270	ED033033	ED032366		ED032894
0.040 (1.0)					ED032895
0.045 (1.1)	ED034271		ED032367		ED032896
0.052 (1.3)	ED034272	ED034430*	ED032368	ED032814	ED032897
1/16 (1.6)	ED034356	ED036220**	ED032968		
Diameter in (mm)	500 lb (227 kg) Infinity-Pak®	900 lb (408 kg) Accu-Pak® Box	1000 lb (454 kg) Infinity-Pak®	1000 lb (454 kg) Accu-Pak® Box	1000 lb (454 kg) Precise-Trak® Reel
0.035 (0.9)	ED034402	ED032861			
0.040 (1.0)					
0.045 (1.1)			ED033215		ED032808
0.052 (1.3)				ED032863	ED032809
1/16 (1.6)				ED032864, ED034431*	
				ED032865	

*Buy America Product **Tested Material

MECHANICAL PROPERTIES⁽¹⁾ – As Required per AWS A5.18/A5.18M

	Yield Strength ⁽²⁾ MPa (ksi)	Tensile Strength MPa (ksi)	Elongation %	Charpy V-Notch J (ft·lbf)	
				@ -29°C (-20°F)	@ -40°C (-40°F)
Requirements – AWS ER70S-6 As-Welded with 100% CO ₂	400 (58) min	485 (70) min	22 min	27 (20) min	Not Specified
Typical Results ⁽³⁾					
As-Welded with 100% CO ₂	455 (66)	565 (82)	28	71 (52)	53 (39)
As-Welded with 75% Ar/25% CO ₂	485 (70)	595 (86)	25	56 (41)	53 (39)
As-Welded with 90% Ar/10% CO ₂	460 (67)	570 (83)	25	75 (55)	65 (48)

⁽¹⁾Typical all weld metal. ⁽²⁾Measured with 0.2% offset. ⁽³⁾See test results disclaimer

WIRE COMPOSITION – As Required per AWS A5.18/A5.18M

	%C	%Mn	%Si	%S	%P
Requirements – AWS ER70S-6	0.06-0.15	1.40-1.85	0.80-1.15	0.035 max	0.025 max
	%Cu ⁽⁴⁾	%Ni	%Cr	%Mo	%V
Requirements – AWS ER70S-6	0.50 max	0.15 max	0.15 max	0.15 max	0.03 max

TYPICAL OPERATING PROCEDURES

Diameter, Polarity Shielding Gas	CTWD ⁽⁵⁾ mm (in)	Wire Feed Speed m/min (in/min)	Voltage (volts)	Approx. Current (amps)	Melt-Off Rate kg/hr (lb/hr)
0.035 in (0.9 mm), DC+					
Short Circuit Transfer 75% Ar/25% CO ₂ ⁽⁶⁾	12 (1/2)	2.5 (100)	17	80	0.7 (1.6)
		3.8 (150)	18	120	1.1 (2.4)
		6.4 (250)	20	175	1.8 (4.0)
Spray Transfer 90% Ar/10% CO ₂	19 (3/4)	9.5 (375)	23	195	2.7 (6.0)
		12.7 (500)	29	230	3.6 (8.0)
		15.2 (600)	30	275	4.4 (9.6)
0.045 in (1.1 mm), DC+					
Short Circuit Transfer 75% Ar/25% CO ₂ ⁽⁶⁾	12 (1/2)	3.2 (125)	18	145	1.5 (3.4)
		3.8 (150)	19	165	1.8 (4.0)
		5.1 (200)	20	200	2.4 (5.4)
Spray Transfer 90% Ar/10% CO ₂	19 (3/4)	8.9 (350)	27	285	4.2 (9.2)
		12.1 (475)	30	335	5.7 (12.5)
		12.7 (500)	30	340	6.0 (13.2)
0.052 in (1.3 mm), DC+					
Spray Transfer 90% Ar/10% CO ₂	19 (3/4)	7.6 (300)	30	300	4.8 (10.6)
		8.1 (320)	30	320	5.2 (11.5)
		12.3 (485)	32	430	7.8 (17.1)
1/16 in (1.6 mm), DC+					
Spray Transfer 90% Ar/10% CO ₂	19 (3/4)	5.3 (210)	25	325	4.8 (10.7)
		6.0 (235)	27	350	5.4 (12.0)
		7.4 (290)	28	430	6.7 (14.8)

⁽¹⁾Typical all weld metal. ⁽²⁾Measured with 0.2% offset. ⁽³⁾See test results disclaimer ⁽⁴⁾Copper due to any coating on the electrode plus the copper content of the filler metal itself, shall not exceed the stated 0.50% max. ⁽⁵⁾CTWD (Contact Tip to Work Distance). Subtract 1/4 in (6.4 mm) to calculate Electrical Stickout. ⁽⁶⁾Procedures in these areas are procedures for short circuiting mode using 75% Argon, 25% CO₂. NOTE: For 100% CO₂ procedures, add 1 to 2 volts for short circuit transfer and 2 to 3 volts for globular transfer.

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.