

# CERTIFICATE OF CONFORMANCE

Product: **SuperArc® L-50®**

Classification: **AWS D1.5 ER70S-3**

Also meets the requirements of **AWS D1.1 ER70S-3**

Date **April 02, 2024**

This is to certify that the product named above is of the same classification(s) and design as the material used for the tests reported herein. The material was tested according to the specification(s) indicated and met all requirements. It was manufactured and supplied according to a Quality System Program that meets the requirements of ISO9001 among others as documented on The Lincoln Electric web page (<http://www.lincolnelectric.com/en-us/company/Pages/certifications.aspx>).

Operating Settings	ER70S-3 Requirements	RESULTS
Electrode Size		.045" (1.1 mm)
Current Type/Polarity	DC+	DC+
Shielding Gas	Not Specified	80% Ar, 20% CO2
Wire Feed Speed, cm/min (in/min)	Not Specified	1092 (430)
Nominal Voltage, V	Not Specified	29.0
Nominal Current, A	Not Specified	300
Average Heat Input, kJ/mm (kJ/in)		1.5 (37.4)
Travel Speed, cm/min (in/min)	Not Specified	36 (14.0)
Contact Tip to Work Distance, mm (in)	Not Specified	19 (3/4)
Pass/Layers		16/6
Preheat Temperature, °C (°F)	(60 min.)	20 (72)
Interpass Temperature, °C (°F)	(325 max.)	135 (275)
Postweld Heat Treatment	As-welded	As-welded
Base Material		ASTM A36 steel

**Mechanical properties of weld deposits**

Tensile Strength, MPa (ksi)	(70 min.)	540 (78)
Yield Strength, 0.2% Offset, MPa (ksi)	(58 min.)	440 (63)
Elongation %	22 min.	25
Average Impact Energy Joules @ -18 °C (ft-lbs @ 0 °F)	(20 min.)	153 (113) 150,150,159 (110,111,118)

**Chemical composition of weld deposits (weight %)**

C	Info. Only	0.10
Mn	Info. Only	0.94
Si	Info. Only	0.45
P	Info. Only	0.008
S	Info. Only	0.009
Ni	Info. Only	0.01
Cr	Info. Only	0.02
Mo	Info. Only	<0.00
V	Info. Only	<0.003
Zr	Info. Only	<0.001
Ti	Info. Only	<0.001
Al	Info. Only	0.00
Cu	Info. Only	0.18

Electrode composition (weight %)	ER70S-3 Requirements	Electrode Results
C	0.06 - 0.15	0.09
Mn	0.90 - 1.40	1.18
Si	0.45 - 0.75	0.63
P	0.025 max.	0.008
S	0.035 max.	0.008
Ni	0.15 max.	0.01
Cr	0.15 max.	0.02
Mo	0.15 max.	<0.00
V	0.03 max.	<0.00
Cu (Total)	0.50 max.	0.18

1. This document meets the requirements of AWS A5.01M/A5.01 Schedule G. When a specific lot number is referenced it also meets the requirements of EN10204, type 2.2. It does not meet the requirements of type 3.1.
2. Radiographic Inspection: Met requirements.
3. Strength values in SI units are reported to the nearest 10 MPa converted from actual data. Preheat and interpass temperature values in SI units are reported to the nearest 5 degrees.

# CERTIFICATE OF CONFORMANCE



Product: **SuperArc® L-50®**  
Classification: **AWS D1.5 ER70S-3**  
Also meets the requirements of **AWS D1.1 ER70S-3**  
Date **April 02, 2024**

A handwritten signature in black ink, appearing to read "Daniel Gaul".

April 02, 2024

Daniel Gaul, Certification Supervisor

Date

A handwritten signature in black ink, appearing to read "Regis Geisler".

April 02, 2024

Regis Geisler, Manager, Consumable Compliance

Date