

STARINOX 308L

TOP FEATURES

- Semi-basic stick electrode suitable for the welding of austenitic steels Cr-Ni steels or cast steels containing 16-20%Cr and 8-12%Ni
- Can also be used for the welding of stainless steels of the same type, whether stabilized or not, for services temperatures up to +350°C.
- The weld deposit has a carbon content <0,04%.
- Easy arc striking and restriking.
- Efficiency 100%.
- Weldable on AC and DC+ polarity.

TYPICAL APPLICATIONS

- Food, nuclear, chemical industry and associated applications.

CLASSIFICATION

AWS A5.4	E308L-16
EN ISO 3581-A	E 19 9 L R 12

CURRENT TYPE

AC, DC+

WELDING POSITIONS

All positions

APPROVALS

ABS	BV	DNV	TÜV	CE
+	+	+	+	+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL

C	Mn	Si	P	S	Cr	Ni	Ferrite
0.025	0.9	0.8	≤0.030	≤0.025	19.8	9.5	5-10

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

Required	Condition*	0.2% Proof strength (MPa)	Tensile strength (MPa)	Elongation (%)	Impact ISO-V (J) +20°C
AWS A5.4	AW	not specified	≥520	≥30	not specified
EN ISO 3581-A	AW	≥320	≥510	≥30	not specified
Typical values	AW	≥320	≥520	≥35	≥60

* AW: As-welded

OUTPUT RANGE

Diameter x Length (mm)	Current range (A)
2.0 x 300	30-60
2.5 x 350	55-80
3.2 x 350	70-110
4.0 x 450	120-140

PACKAGING AND AVAILABLE SIZES

Diameter x Length (mm)	Packaging	Electrodes/pack	Net weight/pack (kg)	Item number
2.0 x 300	VPMD	150	1.8	W100288719
2.5 x 350	VPMD	92	2.0	W100288720
3.2 x 350	VPMD	55	1.9	W100288722
4.0 x 450	VPMD	40	2.7	W100288723

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing.
Please refer to www.lincolnelectric.eu for any updated information.