SuperGlaze® 5356 PLUS

TOP FEATURES

- Premium Spooled 5356 Product
- Optimal for semi-automatic applications
- Stable arc and easy to manipulate puddle.

TYPICAL APPLICATIONS

- General purpose filler alloy for 5XXX and 6XXX series alloys
- Trailer Manufacturing
- Formed truck panels
- Structural frames in the shipbuilding industry

CLASSIFICATION

AWS A5.10 ER5356

EN ISO 18273 S AI 5356 (AIMg5Cr(A))

SHIELDING GASES (ACC. EN ISO 14175)

 I1
 Inert gas Ar (100%)

 I3
 Inert gas Ar + 0.5-95% He

 Flow rate
 14-24 l/min (Argon)

APPROVALS

ABS	LR	BV	DNV	RINA	TÜV	DB	CWB	ccs	OTHER	CE
+	+	+	+	+	+	+	+	+	KR	+

CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, WIRE

Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Be
bal.	0.05	0.09	0.03	0.12	4.90	0.08	<0.01	0.15	0.0002

Notes: Unspecified elements should not exceed a total of 0.15%

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition*	Tensile strength (MPa)	Elongation (%)
Typical values	l1	AW	240-290	16-35

^{*} AW = As welded

PACKAGING AND AVAILABLE SIZES

Wire diameter (mm)	Packaging	Weight (kg)	Item number
1.7	SPOOL (BS300)	7.0	ED704123
1.2	SPOOL (S300)	7.26	ED704124
1.6	SPOOL (BS300)	7.0	ED704125

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.eu for any updated information.

SuperGlaze® 5356 PLUS-EN-04/03/24

